


OKS 571 PTFE Bonded Coating, Spray



Description

PTFE bonded coating for dry lubrication of different material pairs at low pressures, low speeds and in dusty environments.

Applications

- Dry lubrication of the most varied materials sliding on top of or rubbing against each other (such as metals, wood, ceramic, rubber, and also adhesives or paintable plastics)
- Anti-stick coating of seals or sealing surfaces of all kinds to prevent sticking-on
- To cure the squeaking noises of soft on hard materials
- For water-repellent impregnation of absorbent materials
- Separating film in cast resin applications

Advantages and benefits

- Dry, non-soiling film
- Highly effective due to good adhesion to prepared substrates
- Colourless and odourless low-friction coating with non-stick properties
- Prevents frictional corrosion
- Dries at room temperature

Branches

- Shipbuilding and marine technology
- Chemical industry
- Plant and machine (tool) engineering
- Glass and foundry industry
- Rail vehicle technology
- Iron and steel industry
- Logistics
- Municipal services
- Paper and packaging industry
- Rubber and plastic processing



OKS 571
PTFE Bonded Coating, Spray

Application tips

For optimum adhesion, clean the surfaces. Best way is to clean mechanically first and then with OKS 2610/OKS 2611 universal cleaner. The surfaces to be treated must be bright metal and dry. Chemical or mechanical pretreatment of surfaces may extend the service life of the non-stick paint. Stir the paint thoroughly before use. Apply OKS 570 in an evenly thin film to the prepared surfaces, preferably by spraying or dipping, in individual cases also by brush. Spray OKS 571 on evenly. Avoid local excesses (e.g. 'curtaining'). Drying and curing conditions as per the following technical data.

Packaging

- 400 ml Spray

Technical Data

	Standard	Conditions	Unit	Value
Main components				
additives				UV indicator
binder				silicone resin
solid lubricants				PTFE
solvent				solvent mixture
Application related technical data				
colour				whitish
density (at 20°C)	DIN EN ISO 3838		g/cm ³	0.83
drying time		room temperature	min	15
flashing point	DIN 51 755 (-2)	< 65 (< 5°C)	°C	< -18
lower operating temperature			°C	-180
optimal layer thickness	DIN 50 981/50 984	DIN 50 982-2	µm	5-20
press-fit test	draft DIN 51 833		µ	0.07, no chatter
processing temperature			°C	20-25
surface covering			m ² /can	3
thread friction coefficient (µ)	DIN EN ISO 16 047	screw ISO 4017 M10x55-8.8 black-oxide		0.1
thread friction coefficient (µ)	DIN EN ISO 16 047	nut ISO 4032 M10-10 black-oxide		0.1
upper operating temperature			°C	260

OKS Spezialschmierstoffe GmbH

Ganghoferstraße 47
82216 Maisach
Phone: +49 (0) 8142 3051 - 500
info@oks-germany.com
www.oks-germany.com



The information in this publication reflects state-of-the-art technology, as well as extensive testing and experience. Due to the diversity of possible applications and technical realities, they can only serve as recommendations and are not arbitrarily transferable. Therefore, no obligations, liability or warranty claims can be derived from them. We only accept liability for the suitability of our products for particular purposes, and for certain properties of our products, in the event that we have accepted such liability in writing in the individual case. Any case of justified warranty claims shall be limited to the delivery of replacement goods free of defects, in the event that this subsequent improvement fails, to reimbursement of the purchase price. Any and all further claims, in particular the liability for consequential injuries or damage, shall always be excluded. Prior to use, the customer must conduct its own testing to prove suitability. The data are subject to change for the sake of progress. ® = Registered trademark
Safety data sheet for industrial and commercial users is available for downloading under www.oks-germany.com.
Our Customer and Technical service will be pleased to help should you have any further questions.